

## Cut Wire Shot



**Remarkable durability and uniformity contribute to cost reduction, quality improvements, greater reliability, and better environment.**

### Application

shot blasting, shot peening, processes to remove paints, etc.

### Material

Steel, Stainless steel, Aluminum, Zinc, Copper, etc.

### Characteristics

- Good abrasion - improves work efficiency
- Highly durable - reduces manufacturing time and cost
- Stable peening effect because of uniform hardness and particle size
- Low breakage and less dust contribute to better environment. (ISO14001)
- Variety of products available to match the material, hardness, and purpose of the work piece

Material Type	Zinc	Copper	Aluminum		Stainless		Steel			
			Pure	Alloy	SUS430	SUS304	SWRH42A-SWRH82A			
Hardness(HV)	33-55	100-150	40-60	80-	250-450	400-600	100-300	300-400	400-500	500-600
Size (mm)	0.3					○			○	○
	0.4					○			○	○
	0.5					○			○	○
	0.6			○	○	○	○	○	○	○
	0.7						○	○	○	○
	0.8	○		○	○	○	○	○	○	○
	1.0	○		○	○	○	○	○	○	○
	1.2	○	○	○	○	○	○	○	○	○
	1.5	○	○	○		○	○	○	○	○
1.7	○	○			○	○	○	○		
2.0	○	○			○	○	○	○		

- Maximum diameter. 3.0mm
- Standard size (diameter) is listed above
- Please feel free to contact us if your requirements for size, hardness, material, etc, are special and not listed above.



#### **TOYO SEIKO CO.,LTD.**


3-195-1 Umaganji Yatomi City, Aichi Prefecture  
 TEL: +81 567-52-3451 FAX: +81 567-52-3457

#### **TOYO SEIKO (THAILAND) CO.,LTD.**

802 Moo4, Bangpoo Industrial Estate, Soi 14, Sukhumvit Road, Praeksa, Muang, Samutprakarn 10280  
 TEL: +66 2 324 0046 FAX: +66 2 324 0047

URL <http://www.toyoseiko.co.jp>

 [toyotoyoseiko.co.jp](mailto:toyotoyoseiko.co.jp)

 [info@toyoseiko.co.th](mailto:info@toyoseiko.co.th)