*Device image is for illustration purposes.

COVERAGE CHECKER

TOYOSEIKO

Outline / Feature

Coverage Checker is designed for easy and precise coverage measurement instead of human eyes. UV light version measures coverage by the fluorescent paint peeling rate, using 375nm UV light. This enables to measure the coverage of surface which was difficult to measure with normal type TOYO SEIKO Coverage Checker.

asurement Device

- A surface that already has peened indentations, such as double shot peening.
- Surfaces that are not easily indented, such as carburized parts.

/ light version

Surface with the oxidation scale by heat treatment.

Surface example of fluorescent paint applied after 1st shot peening, getting ready for 2nd shot peening

Q Function

- Easy to create recipes (measurement conditions). One recipe for one fluorescent paint will be enough.
- Automatically displays the coverage% of the camera positioned surface.
- Measurement record history are saved automatically, and are able to search. Captured images can be saved in BMP format.
- DUST & DRIP-PROOF camera Protects the camera body from dust and water drops during outdoor operation.






Automatically displayed coverage
Measurment record history



World Leading Company for Shot Peening 3-195-1 Umaganji, Yatomi-city , Aichi 490-1412 , Japan TEL +81-567-52-3451 E-mail toyo@toyoseiko.co.jp Able to measure curved surface (min φ 10mm)

VERAGE CHECKER







Size	L190 x W55 x 55mm
Light source	UV LED light (wavelength 375nm)
Fluorescent paint	Fluorescent paint excited by 375nm light source
Measuring surface size	4.8 x 3.6mm (640 x 480 pixel)
Measurable curvature	min φ10mm
OS	Windows 10

World Leading Company for Shot Peening Media

3585 Moreau Court, South Bend, Indiana 46628, USA TEL +1-574-288-2000 E-mail sales@toyoseiko-na.com